

METEOR 70



Elegant Oak - Natural

Fiber Wood



Elegant Oak



Cliff Oak



TECHNICAL DATA	STANDARDS	METEOR 70
Classification		
Type of floor covering	ISO 10582	Heterogeneous Compact Vinyl
Classification	ISO 10874 (EN 685) commercial industrial	Classes: 34 43
Characteristics		
Total thickness	ISO 24346 (EN 428)	2.00mm
Wear layer thickness	ISO 24340 (EN 429)	0.70mm
Total weight	ISO 23997 (EN 430)	2 650g/m ²
PU treatment	-	TopClean™
Wear layer binder content	ISO 10582	Type I
Technical performance		
Residual indentation	Average measured value ISO 24343-1 (EN 433) requirement	0.04mm ≤ 0.10mm
Reaction to fire	EN 13501-1	B _s -s1 Glued on derivative wood panel
Slip resistance	DIN 51130 EN 13893	R10 μ ≥ 0.30
Dimensional stability	ISO 23999 (EN 434)	≤ 0.10%
Furniture leg	EN 424	No damage
Castor wheel test	ISO 4918 (EN 425)	No damage
Curl resultant to heat	ISO 23999 (EN 434)	≤ 8mm
Electrostatic properties	EN 1815 EN 1081	≤ 2kV on concrete R1 > 10 ⁹ ohms
Chemical resistance	ISO 26987 (EN 423)	High resistance
Hygiene	-	Does not contribute to infection spreading
Thermal resistance Underfloor heating	EN ISO 10456	0.02m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6
Impact Sound Resistance	Standards EN ISO 10140-3 EN ISO 717/2	ΔLw = 7dB

The above information is subject to modifications for the benefit of further improvement (02/2017).
For more detailed technical information, please contact Tarkett.

Elegant Oak



METEOR 70 Wood

Main Product Features

- Colours combinations between all-over designs and uni shades
- Available in 2 and 4 meter widths

Surface Treatment



Sustainability Tag



Logistics Information



Available in rolls:
2m & 4m
Rolls length: 231m

Laying direction:



General Information




According to European
Classification ISO 10874 (EN 685)

METEOR 70



Rock Mineral - Anthracite

Stylish Concrete



Light Grey

2510 4008
2510 3008



Grey

2510 4009
2510 3009



Beige

2510 4010
2510 3010



Dark Grey

2510 4011
2510 3011

Fossil



Light Grege

2510 4012
2510 3012



Grey

2510 4013
2510 3013



Grege

2510 4014
2510 3014



Dark Grey

2510 4015
2510 3015

Rock Mineral



Light Grege

2510 4016
2510 3016



Grey

2510 4017
2510 3017



Dark Grey

2510 4018
2510 3018

TECHNICAL DATA	STANDARDS	METEOR 70
Classification		
Type of floor covering	ISO 10582	Heterogeneous Compact Vinyl
Classification	ISO 10874 (EN 685) commercial industrial	Classes: 34 43
Characteristics		
Total thickness	ISO 24346 (EN 428)	2.00mm
Wear layer thickness	ISO 24340 (EN 429)	0.70mm
Total weight	ISO 23997 (EN 430)	2 650g/m ²
PU treatment	-	TopClean™
Wear layer binder content	ISO 10582	Type I
Technical performance		
Residual indentation	Average measured value	0.04mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm
Reaction to fire	EN 13501-1	B _s -s1 Glued on derivative wood panel
Slip resistance	DIN 51130 EN 13893	R10 μ ≥ 0.30
Dimensional stability	ISO 23999 (EN 434)	≤ 0.10%
Furniture leg	EN 424	No damage
Castor wheel test	ISO 4918 (EN 425)	No damage
Curl resultant to heat	ISO 23999 (EN 434)	≤ 8mm
Electrostatic properties	EN 1815 EN 1081	≤ 2kV on concrete R1 > 10 ⁹ ohms
Chemical resistance	ISO 26987 (EN 423)	High resistance
Hygiene	-	Does not contribute to infection spreading
Thermal resistance Underfloor heating	EN ISO 10456	0.02m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6
Impact Sound Resistance	Standards EN ISO 10140-3 EN ISO 717/2	ΔLw = 7dB

The above information is subject to modifications for the benefit of further improvement (02/2017).
For more detailed technical information, please contact Tarkett.

Rock Mineral



Anthracite

2510 4019
2510 3019

METEOR 70

Stylish Concrete: Fossil/Rock Mineral

Main Product Features

- Colours combinations between all-over designs and uni shades
- Available in 2 and 4 meter widths

Surface Treatment



Sustainability Tag



Logistics Information



Available in rolls:
2m & 4m
Rolls length: 231m

Laying direction:



General Information



According to European
Classification ISO 10874 (EN 685)

METEOR 55



Practicality and value
that are perfect for
semi-commercial spaces

SENSORY


- Available in 2 and 4 meter widths
- Harmonious chip decors

ENVIRONMENTAL BENEFITS

- REACH Compliant
- Low VOC emissions contribute to better indoor air quality

FUNCTIONAL BENEFITS

- Good underfoot & acoustic comfort
- Easy to maintain
- Competitively priced



METEOR 55

- 1 Easy maintenance and very high resistance to scratches:
TopClean™ PUR reinforcement treatment
- 2 Resistance to abrasion:
0.55mm pure PVC transparent wear layer
- 3 High definition print
- 4 Superior dimensional stability (≤ 0.40%):
glass fibre non-woven reinforcement
- 5 Resistance to indentation and tearing:
solid homogeneous calendared sheet made of recycled vinyl
- 6 PVC Backing

TECHNICAL DATA	STANDARDS	METEOR 55
Classification		
Type of floor covering	ISO 10582	Heterogeneous Compact Vinyl
Classification	ISO 10874 (EN 685) commercial industrial	Classes: 34 43
Characteristics		
Total thickness	ISO 24346 (EN 428)	2.00mm
Wear layer thickness	ISO 24340 (EN 429)	0.55mm
Total weight	ISO 23997 (EN 430)	2300g/m ²
PU treatment	-	TopClean™
Wear layer binder content	ISO 10582	Type I
Technical performance		
Residual indentation	Average measured value	0.05mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm
Reaction to fire	EN 13501-1	B _s -s1 glued on derivative wood panel
Slip resistance	DIN 51130 EN 13893	R10 μ ≥ 0.30
Dimensional stability	ISO 23999 (EN 434)	≤ 0.10%
Castor wheel test	ISO 4918 (EN 425)	No damage
Curl resultant to heat	ISO 23999 (EN 434)	≤ 8mm
Electrostatic properties	EN 1815 EN 1081	≤ 2kV on concrete R1 > 10 ⁹ ohms
Chemical resistance	ISO 26987 (EN 423)	High resistance
Hygiene	-	Does not contribute to infection spreading
Thermal resistance Underfloor heating	EN ISO 10456	0.02m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6
Impact sound reduction	EN ISO 10140-3 EN ISO 717/2	ΔL _w = 13dB
Form of delivery		
Form of delivery	EN 24341 (EN 426)	approx. 23lm x 2/4m
Colours		26

The above information is subject to modifications for the benefit of further improvement (02/2017).
For more detailed technical information, please contact Tarkett.

METEOR 55



Fiber Wood - Grege



Fiber Wood



Elegant Oak



Cliff Oak



TECHNICAL DATA	STANDARDS	METEOR 55
Classification		
Type of floor covering	ISO 10582	Heterogeneous Compact Vinyl
Classification	ISO 10874 (EN 685) commercial industrial	Classes: 34 43
Characteristics		
Total thickness	ISO 24346 (EN 428)	2.00mm
Wear layer thickness	ISO 24340 (EN 429)	0.55mm
Total weight	ISO 23997 (EN 430)	2300g/m ²
PU treatment	-	TopClean™
Wear layer binder content	ISO 10582	Type I
Technical performance		
Residual indentation	Average measured value	0.05mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm
Reaction to fire	EN 13501-1	B _s -s1 glued on derivative wood panel
Slip resistance	DIN 51130 EN 13893	R10 μ ≥ 0.30
Dimensional stability	ISO 23999 (EN 434)	≤ 0.10%
Castor wheel test	ISO 4918 (EN 425)	No damage
Curl resultant to heat	ISO 23999 (EN 434)	≤ 8mm
Electrostatic properties	EN 1815 EN 1081	≤ 2kV on concrete R1 > 10 ⁹ ohms
Chemical resistance	ISO 26987 (EN 423)	High resistance
Hygiene	-	Does not contribute to infection spreading
Thermal resistance Underfloor heating	EN ISO 10456	0.02m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6
Impact sound reduction	EN ISO 10140-3 EN ISO 717/2	ΔL _w = 13dB

The above information is subject to modifications for the benefit of further improvement (02/2017).
For more detailed technical information, please contact Tarkett.

Elegant Oak



METEOR 55 Wood

Main Product Features

- Comfortable floor with 10dB acoustic
- Available in 2 and 4 meter widths
- Wood

Surface Treatment



Sustainability Tag



Logistics Information



Laying direction:



General Information



According to European
Classification ISO 10874 (EN 685)

METEOR 55



Stylish Concrete - Grey



Stylish Concrete



Fossil



Rock Mineral



TECHNICAL DATA	STANDARDS	METEOR 55
Classification		
Type of floor covering	ISO 10582	Heterogeneous Compact Vinyl
Classification	ISO 10874 (EN 685) commercial industrial	Classes: 34 43
Characteristics		
Total thickness	ISO 24346 (EN 428)	2.00mm
Wear layer thickness	ISO 24340 (EN 429)	0.55mm
Total weight	ISO 23997 (EN 430)	2300g/m ²
PU treatment	-	TopClean™
Wear layer binder content	ISO 10582	Type I
Technical performance		
Residual indentation	Average measured value	0.05mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10mm
Reaction to fire	EN 13501-1	B _s -s1 glued on derivative wood panel
Slip resistance	DIN 51130 EN 13893	R10 μ ≥ 0.30
Dimensional stability	ISO 23999 (EN 434)	≤ 0.10%
Castor wheel test	ISO 4918 (EN 425)	No damage
Curl resultant to heat	ISO 23999 (EN 434)	≤ 8mm
Electrostatic properties	EN 1815 EN 1081	≤ 2kV on concrete R1 > 10 ⁹ ohms
Chemical resistance	ISO 26987 (EN 423)	High resistance
Hygiene	-	Does not contribute to infection spreading
Thermal resistance Underfloor heating	EN ISO 10456	0.02m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6
Impact sound reduction	EN ISO 10140-3 EN ISO 717/2	ΔL _w = 13dB

The above information is subject to modifications for the benefit of further improvement (02/2017).
For more detailed technical information, please contact Tarkett.

Rock Mineral



2510 6019
2510 5019

METEOR 55

Concrete and Mineral

Main Product Features

- Comfortable floor with 10dB acoustic
- Available in 2 and 4 meter widths
- Wood

Surface Treatment



Sustainability Tag



Logistics Information



Available in rolls:
2m & 4m
Rolls length: 231m

Laying direction:



General Information



According to European
Classification ISO 10874 (EN 685)